

# Planibel Clear

Discover the ideal glass transparency with Planibel Clear! Adequate for use in numerous sectors, be it in construction, decoration, automotive or high-tech!



You have printed

Linea Azzurra

**AGC**

A light blue arrow points from the left edge of the page towards the 'Planibel Clear' title.

# Planibel Clear

Discover the ideal glass transparency with Planibel Clear! Adequate for use in numerous sectors, be it in construction, decoration, automotive or high-tech!

## The brand Planibel Clear

### Clear base glasses

Clear benchmark glasses that can be processed in all ways for use in numerous sectors, including the construction, decoration, automotive and high-tech industries Planibel clear base glasses are made using the 'float' process: the sides of the glass are perfectly flat and parallel Transparency: high light transmission Base glass to which coatings are applied

Application :single glazing - insulating glazing - laminated glass - toughened glass - enamelled glass - sandblasted glass

## Planibel Clear

Discover the ideal glass transparency with Planibel Clear! Adequate for use in numerous sectors, be it in construction, decoration, automotive or high-tech!

### Linea Azzurra

Clear glass available in large thicknesses. In this case it features a blue tint

Ideal for use in large glazed areas and high-quality furniture and decoration



## Performances

### Linea Azzurra

Structure	Light properties (EN 410)		Thermal properties (EN 673)			Ug-Value W/(m².K)
	LT %	LR %	EA %	SF %	SC %	
10	86	8	24	75	0.86	5.6
12	85	8	28	73	0.84	5.5
15	83	8	33	69	0.79	5.5
19	81	7	38	66	0.76	5.4
25	78	7	44	61	0.7	5.2
8	87	8	20	78	0.9	5.7



# Planibel Clear

Discover the ideal glass transparency with Planibel Clear! Adequate for use in numerous sectors, be it in construction, decoration, automotive or high-tech!

Click on the row of your choice to go straight to the product performances.

## Abbreviations:

LT: Light Transmission; LR: Light Reflection; UV: Ultraviolet transmission; EA: Energy Absorption; SF: Solar Factor. Symbols: The | symbol indicates the position of the solar-control coating.

- The | symbol indicates the position of a low-emissivity coating (Planibel Top N+ or Top N+T).
- The ! Symbol indicates the position of a low-emissivity coating (Planibel G)

## Tolerances:

The data are calculated using spectral measurements that are conform to standards EN 410 (1998). The tolerance of published data with respect to photometric properties is +/- 3 points. The U-value (formerly k-value) is calculated according to standard EN 673. The emissivity measurement complies with standards EN 673 (Annex A) and EN 12898. The U-value tolerance is +/- 0.1W/(m<sup>2</sup>.K).

This information is no evaluation of the risk of glass breakage due to thermal stress. See also conditions of use.